



BEMAC LABORATORIES

A Subsidiary of Mahaffey Associates Pty Ltd ABN 90 001 629 036
4 Mary Parade Rydalmere NSW 2116
PO Box 349 Rydalmere BC NSW 1701
Phone: (02) 9684 2422 Fax: (02) 9684 2310
Email: bemac@mahaffey.com.au

Test: Compressive Strength Testing Of Masonry
Method: AS3700 2001
Client : Timbercrete
Job Number : 8264
Unit Type: Timbercrete 90 x 90 x 290 Assembled 3 High
Unit Material: Timbercrete
Bed Joint Thickness: 10mm
Bed Joint Material: Not Advised

Sample Conditioning: Nil
Pattern and Direction of Coring: Nil
Orientation of Units: As Laid (See Note 3)
Capping: Masonite Full Face
Sampled by: Client
Sampling Date for Units: Not Advised
Assembled by: Client
Assembly Date: 01-Apr-07
Test Date: 7-May-07

Specimen ID	Dimensions (mm)			Load (kN)	Aspect Ratio	Aspect Ratio Factor (K _a)	Unconfined Compressive Strength (MPa)
	W	L	H				
1	90	290	300	133.8	3.3	0.88	4.5
2	90	290	300	131.1	3.3	0.88	4.4
3	90	290	300	123.1	3.3	0.88	4.1
SD							0.2
Mean							4.3

David Wilmsurst
Approved Signatory
10/05/2007

Note 1: Working Dimensions noted above, and used for calculations
Note 2: This Document shall not be reproduced except in full