



BEMAC LABORATORIES

A Subsidiary of Mahaffey Associates Pty Ltd ABN 90 001 629 036
4 Mary Parade Rydalmere NSW 2116
PO Box 349 Rydalmere BC NSW 1701
Phone: (02) 9684 2422 Fax: (02) 9684 2310
Email: bemac@mahaffey.com.au

This document is issued in accordance
with NATA's accreditation requirements.
credited for compliance with ISO/IEC 17025
Accreditation No. 1393



Test: Compressive Strength Testing Of Mortar Cubes
Method: Based on AS1012.9
Client : Timbercrete
Job Number : 8264
Material: Mortar

Manufacturing Date: 1-Apr-07
Test Date: 7-May-07
Sample Conditioning: Nil
Capping: Masonite Full Face
Sampled by: Client

| Specimen ID | Dimensions (mm) | | | Load (kN) | Compressive Strength (MPa) |
|-------------|-----------------|------|----|-------------|----------------------------|
| | W | L | H | | |
| 1 | 103.7 | 96.8 | 90 | 30.2 | 3.0 |
| 2 | 102.6 | 94.1 | 90 | 25.9 | 2.7 |
| 3 | 103.7 | 96.0 | 90 | 26.9 | 2.7 |
| | | | | SD | 0.0 |
| | | | | Mean | 0.0 |

Note 1: Actual Dimensions used

Note 2: This Document shall not be reproduced except in full

David Wilmshurst
Approved Signatory
10/05/2007